

# DuPont™ Vertrel® XF

## Specialty Fluid

### Introduction

Vertrel® XF is a proprietary hydrofluorocarbon fluid with “zero” ozone depletion and a low global warming potential ideally suited for use in vapor degreasing equipment for cleaning, rinsing, and drying. It can replace current hydrochlorofluorocarbon (HCFC) and perfluorocarbon (PFC) fluids in most applications.

Vertrel® XF is HFC 43-10mee or 2,3-dihydrodecafluoropentane; empirical formula  $C_5H_2F_{10}$ . It is a clear, colorless liquid with the properties shown in **Tables 1–2**.

Unique physical properties include a high density, low viscosity, and low surface tension. This combined with nonflammability, chemical and thermal stability, low toxicity, and ease of recovery by distillation make Vertrel® XF ideal for a broad range of applications. Solvency is selective, but can be enhanced by use of appropriate azeotropes and blends with alcohols, hydrocarbons, esters, etc. (see **Table 3**).

**Table 1**  
**Physical Properties**

Property <sup>a</sup>	Vertrel® XF
Molecular Weight	252
Boiling Point, °C (°F)	55 (130)
Vapor Pressure, mm Hg (psia)	226 (4.4)
Freezing Point, °C (°F)	-80 (-112)
Liquid Density, g/cc (lb/gal)	1.58 (13.2)
Surface Tension, dyn/cm	14.1
Viscosity, cPs	0.67
Solubility in Water, ppm	140
of Water, ppm	490
Critical Temperature, °C (°F)	181 (357)
Critical Pressure, psia (atm)	331.9 (22.6)
Critical Volume, cc/mol	433
Heat of Vaporization (at boiling point), cal/g (Btu/lb)	31.0 (55.7)
Specific Heat, cal/g°C (Btu/lb°F)	0.27 (0.27)
Dielectric Constant	7-10
Breakdown Voltage, kV	
Liquid	14-28
Vapor	10-12
Volume Resistivity, ohm-cm	$10^9 - 10^{11}$
Flash Point	
Closed Cup <sup>b</sup>	None
Open Cup <sup>c</sup>	None
Flammable Range in Air	None

<sup>a</sup> At 25°C (77°F) except where indicated.

<sup>b</sup> Pensky-Martens Closed Cup Tester (ASTM D 93)

<sup>c</sup> Tag Open Cup Tester (ASTM D 1310)

### Typical Applications

- Cleaning and rinsing agent
- Drying fluid
- Particulate remover
- Fluorocarbon lubricant carrier
- Solvent and dispersion media
- Heat transfer media
- Dielectric fluid
- Replacement for many HCFC, PFC, and CFC-113 applications

Vertrel® XF is ideally suited for cleaning fine particulate matter (submicron range) from metal and nonmetal parts. Removal of particle contamination requires a solvent that can minimize the thickness of the laminar boundary layer where particles are bonded to the substrate. If the boundary layer thickness is less than the particle diameter, momentum from the flowing solvent can efficiently dislodge the particles and carry them away. Vertrel® XF, with its lower viscosity and higher density, results in a thinner boundary layer, which enhances cleaning. Common aqueous cleaning fluids, mixtures of water and detergent, have higher viscosities and lower densities compared to Vertrel® XF, making these fluids less efficient.

The electronic attraction between particle and surface can be overcome further by increasing the polarity of the fluid through the addition of small amounts of alcohols. DuPont offers a series of proprietary azeotrope and blend compositions which exploit this property (see **Table 3**).

Another common cleaning technique is the addition of ultrasonics to the solvent. High frequency, ultrasonic waves produce tiny bubbles which form and collapse (cavitate) as the wave passes. Cavitation energy increases with decreasing viscosity, another advantage of Vertrel® XF, improving its ability to mechanically dislodge particle contamination.

### Vapor Degreasing Process

Use of modern vapor containment technology is recommended for both batch and in-line equipment. These systems have higher freeboard and a secondary set of low-temperature (-29°C [-20°F]) condenser coils to greatly reduce vapor losses from boiling solvent degreasing, defluxing, rinsing, and drying equipment.

Neat Vertrel® XF can be used for rinsing, drying, and some cleaning applications, but use with other components, such as azeotropes or simple blends, can provide improved solvency and soil removal. Vertrel® XF forms azeotropes or constant boiling mixtures with many similar boiling range components. Five nonflammable proprietary azeotrope compositions have been developed that are useful for general and precision cleaning and defluxing. See specific product bulletins for details.



*The miracles of science™*

**Table 2**  
Density and Vapor Pressure Change  
with Temperature

Temperature, °C (°F)	Density, g/cc (lb/g)	Vapor Pressure, mmHg (psia)
-20 (-4)	1.70 (14.2)	16 (0.3)
-10 (14)	1.68 (14.0)	36 (0.7)
0 (32)	1.66 (13.8)	62 (1.2)
10 (50)	1.62 (13.5)	109 (2.1)
20 (68)	1.60 (13.3)	176 (3.4)
30 (86)	1.57 (13.1)	284 (5.5)
40 (104)	1.55 (12.9)	434 (8.4)
50 (122)	1.51 (12.6)	641 (12.4)
60 (140)	1.49 (12.4)	921 (17.8)
70 (158)	1.46 (12.2)	1288 (24.9)
80 (176)	1.43 (11.9)	1753 (33.9)
90 (194)	1.40 (11.7)	2343 (45.3)
100 (212)	1.38 (11.5)	3072 (59.4)
110 (230)	1.34 (11.2)	3961 (76.6)
120 (248)	1.32 (11.0)	5032 (97.3)
130 (266)	1.30 (10.8)	6309 (122.0)

**Table 3**  
Azeotropes of Vertrel® XF

Product	Vertrel® XF With	Boiling Point, °C (°F)
Vertrel® XM	Methanol	46 (115)
Vertrel® XE	Ethanol	52 (126)
Vertrel® XP	Isopropanol	52 (126)
Vertrel® MCA	Trans-1,2-Dichloroethylene	39 (102)
SMT	Trans-1,2-Dichloroethylene and Methanol	37 (99)

## Co-solvent Process

The co-solvent process is a cleaning process that uses a high-boiling, low-volatility solvating agent in combination with Vertrel® XF, in a two-sump vapor degreaser. Parts are immersed into the boil sump containing the solvating agent blended with Vertrel® XF. Parts are then held over the boil sump and optionally sprayed to remove loose contaminants and the solvating agent. The rinse sump contains only Vertrel® XF. Parts are immersed in the rinse sump with optional ultrasonics where final traces of soil and solvating agent are removed. The parts are then held in the vapor zone to complete the drying cycle.

Vertrel® XF is ideally suited for the co-solvent process, because the typical solvating agents are partially to completely miscible with Vertrel® XF, greatly improving the overall cleaning and rinsing efficiency. **Table 4** is a partial list of typical solvating agents. Where the solvating agent is flammable, use of a co-solvent system ameliorates the flammability hazard by providing an inert vapor blanket.

## Solvency

Unlike the PFCs, Vertrel® XF is completely miscible with most esters, ketones, ethers, ether-alcohols, and the lower alcohols, such as methanol, ethanol, and isopropanol. The lower hydrocarbons, such as hexane and heptane, are also soluble. Neat Vertrel® XF has

limited solvency for many higher molecular weight materials, such as hydrocarbon oils, silicone oils, waxes, and greases; here combinations with the many readily miscible esters, alcohols, and lower hydrocarbons can enhance solubility and cleaning efficiency. Like CFC-113 and the PFCs, Vertrel® XF has high solubility for Krytox® and “Fomblin” fluorocarbon lubricants and can be used either as an application carrier fluid or to remove them.

**Table 4**  
Vertrel® XF Solvating Agents

Dibasic Esters (DBE)	Aliphatic Alcohols
Aliphatic Hydrocarbons	Methyl Decanoate
Propylene Glycol N-Propyl	Diisobutyl DBE
N-Methyl-2-Pyrrolidone (NMP)	Isopropyl Myristate
Dipropylene Glycol Butyl Ether	
Dipropylene Glycol Monomethylether	
Tetrahydrofurfuryl Alcohol (THFA)	

## Plastic and Elastomer Compatibility

A large variety of plastics and elastomers can be safely exposed to Vertrel® XF. **Tables 5 and 6** summarize test results on short-term exposures of unstressed plastics and elastomers which simulate a typical cleaning cycle.

Long-term compatibility data simulating exposure of vapor degreaser construction materials is available from DuPont upon request.

Elastomer swelling and shrinking will, in most cases, revert to within a few percent of original size after air drying. Swell, shrinkage, and extractables are strongly affected by the compounding agents, plasticizers, and curing used in the manufacture of plastics and elastomers. Therefore, prior in-use testing is particularly important.

**Table 5**  
Plastic Compatibility  
Immersion: 15 Minutes at Room Temperature

Compatible	
Polyethylene	ABS
Polypropylene	Acetal
Polystyrene	Epoxy
Polyester, PET, PBT	Ionomer
Polyphenylene Oxide, PPO	Liquid Crystal Polymer
Polyimide, PI, PEI, PAI	Phenolic
Polyetherketone, PEK	PVC, CPVC
Polyaryletherketone, PEEK	PTFE, ETFE
Polysulfone	
Polyarylsulfone	
Polyphenylene Sulfide, PPS	
Incompatible <sup>a</sup>	
Acrylic	Cellulosic

<sup>a</sup> Material composition varies depending upon compounding agents, plasticizers, processing, etc. Specific materials should be tested for compatibility with solvent.

**Table 6**  
**Elastomer Compatibility**  
**Immersion: 15 Minutes at Room Temperature**

Compatible	
Buna N, NBR, Nitrile	Buna S, SBR, GRS
Butyl Rubber, IIR	Chlorosulfonated PE
EPM, EPDM, Nordel®	Polysulfide
Natural Rubber, Isoprene	Neoprene
Urethane	Viton® B
	Silicone
Incompatible <sup>a</sup>	
None Tested	

<sup>a</sup> Material composition varies depending upon compounding agents, plasticizers, processing, etc. Specific materials should be tested for compatibility with solvent.

## Metals and Other Compatibility

Vertrel® XF is fully compatible with the metals listed below after exposure for two weeks at 100°C (212°F) in sealed tubes with and without water contact.

- Zinc\*
- Aluminum
- Stainless Steel
- Copper\*
- Brass\*

Vertrel® XF is not compatible with strong bases; therefore, contact with highly basic process materials is not recommended.

\*Slight discoloration with water present

## Exposure Limits

Data from acute toxicity studies has demonstrated that Vertrel® XF has low toxicity. Vertrel® XF is a slight skin and eye irritant and has low acute inhalation toxicity. **Table 7** shows the applicable exposure limits for Vertrel® XF.

**Table 7**  
**Exposure Limits**

Component	Limit, ppm	Type
Vertrel® XF	AEL <sup>a</sup> 200 400	8- and 12-hr TWA Ceiling <sup>b</sup>

<sup>a</sup> AEL (Acceptable Exposure Limit) is an airborne inhalation exposure limit established by DuPont that specifies time-weighted average concentrations to which nearly all workers may be repeatedly exposed without adverse effects.

<sup>b</sup> A ceiling limit is the concentration that should not be exceeded during any part of the working day. The ceiling limit for individual components applies to a blend product as well.

## Safety/Flammability

Vertrel® XF is nonflammable and does not become flammable during boiling or evaporation. It exhibits no closed or open cup flash point, and is not classified as a flammable liquid by NFPA or DOT. It is thermally stable to 300°C (572°F) and does not oxidize or degrade during storage.

## Recovery

Vertrel® XF is a pure component material, and is easily recoverable by off-line and in-line distillation equipment such as a vapor degreaser or still. The presence of soil, however, may alter the characteristics of the material during the recovery operation. Recovery should be closely monitored to ensure operating levels are maintained. Users should test the spent Vertrel® XF to ensure proper classification for waste disposal.

## Storage/Handling

Vertrel® XF is thermally stable and does not oxidize or degrade during storage. Store in a clean, dry area. Protect from freezing temperatures. Do not allow stored product to exceed 52°C (125°F) to prevent leakage or potential rupture of container from pressure and expansion.

Consideration should be given to retrofit of existing, or purchase of new, vapor degreasing equipment to provide vapor containment technology that enables safe and economical use of Vertrel® XF.

Drum pumps are recommended to dispense Vertrel® XF from its container. Refer to the Material Safety Data Sheet for specific handling precautions and instructions.

## Environmental Legislation

Vertrel® XF has “zero” ozone depletion potential and a low global warming potential (**Table 8**). Vertrel® XF and its azeotropes and blends are used as alternatives to CFC-113, methylchloroform, hydrochlorofluorocarbons (HCFCs), and perfluorocarbons (PFCs) in many critical cleaning, drying, carrier fluid, and other high-value specialty uses where reliability is paramount.

Vertrel® XF is accepted by the U.S. Environmental Protection Agency (EPA) under the Significant New Alternatives Policy (SNAP) program as a substitute for ozone-depleting substances. HFC 43-10mee or decafluoropentane is exempt from classification as a volatile organic compound (VOC) by the EPA. Vertrel® XF is also VOC compliant under the California South Coast Air Quality Management District (SCAQMD) regulations, which require VOC content less than 50 g/L of solvent.

Vertrel® XF and its various blend components are listed in most country chemical inventories, such as TSCA in the U.S., ELINICS in Europe, Chemical Substances Control Law (MITI/MHW) in Japan, DSL (notified) in Canada, NICNAS in Australia, and TCCL in Korea.

Vertrel® XF is not a hazardous air pollutant (HAP), and therefore not subject to NESHAP regulation. Spent Vertrel® XF is not a RCRA characteristic or listed waste. However, addition of contaminants could change that status. Vertrel® XF is not included in the SARA Title III Section 313 list of toxic chemicals, and is not subject to SARA Title III (EPCRA) reporting requirements.

## Packaging and Availability

Vertrel® XF is commercially available in 55-gal (208-L) drums with a net weight of 660 lb (299 kg) and in 5-gal (20-L) pails with a net weight of 60 lb (27 kg). One-gallon and smaller samples in glass containers are available on request. Customers are encouraged to secure samples now for compatibility and performance testing.

## Specifications

Composition and specifications are shown in **Table 9**. Vertrel® XF is listed in the TSCA Inventory.

**Table 8**  
**Environmental Properties**

Property	Vertrel® XF
Formula	C <sub>5</sub> H <sub>2</sub> F <sub>10</sub>
Class	Hydrofluorocarbon (HFC)
Atmospheric Lifetime, yr	17.1
Ozone-Depletion Potential (ODP)	0
Global Warming Potential (GWP/100 yr ITH)	1300
Volatile Organic Compounds (VOC, g/L)	Exempt

**Table 9**  
**Vertrel® XF Specifications**

Fluoropentanes, wt%	99.9 min.
Nonvolatile Residue, ppm wt	2.0 max.
Moisture, ppm wt	50 max.
Acidity, mg KOH/g	0.01 max.
Appearance	Clear, Colorless

### North America, Canada, Mexico

Micro Care Marketing Services  
595 John Downey Drive  
New Britain, CT 06051  
Tel: (888) 595-4525  
Fax: (860) 827-8105



### Europe, Africa, Middle East

DuPont de Nemours International S.A.  
2 Chemin du Pavillon  
P.O. Box 50  
CH-1218 Le Grand-Saconnex  
Geneva, Switzerland  
41-22-717-5111

### South America

DuPont do Brasil S.A.  
Alameda Itapecuru, 506  
Alphaville 06454-080 Barueri  
Sao Paulo, Brazil  
55-11-7266-8263

### Pacific

DuPont Australia  
P.O. Box 930  
North Sydney, NSW  
Australia 2060  
61-2-923-6165

### Japan

DuPont-Mitsui Fluorochemicals Co., Ltd.  
Chiyoda Honsha Bldg.  
5-18 Sarugaku-cho 1-Chome  
Chiyoda-Ku, Tokyo 101,  
Japan  
(03) 5281-5805

### Asia

DuPont Taiwan  
P.O. Box 81-777  
Taipei, Taiwan  
886-2-514-4400

DuPont Asia Pacific, Ltd.  
P.O. Box TST 98851  
Tsim Sha Tsui  
Kowloon, Hong Kong  
852-734-5345

DuPont Thailand  
G.P.O. Box 2398  
Bangkok 10500, Thailand  
66-2-236-0026

DuPont Far East, Inc.  
8/F Solid Bank Bldg.  
777 Paseo de Roxas  
Makati 1226 Philippines  
63-2-818-9911

DuPont Far East Inc.  
P.O. Box 7882  
40702 Shah Alam, Malaysia  
60-3-519-3006

DuPont Korea Ltd.  
C.P.O. Box 5972  
Seoul, Korea  
82-2-721-5114

DuPont Singapore Pte. Ltd.  
1 Maritime Square #07 01  
World Trade Centre  
Singapore 0409  
65-273-2244

The information set forth herein is based on data believed to be reliable, but the DuPont Company makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patent.

